

## UPM220E

### Photo Paper Matte for Solvent

Item	Unit	Value	Test Method
<b>Base Material</b>		paper	
<b>Substrate thickness</b>	Micron	160	/
<b>PE lamination thickness</b>	Micron	20 on each side	
<b>Coating thickness</b>	Micron	20+5	
<b>Total thickness</b>	Micron	220+5	
<b>Total weight</b>	gsm	225	
<b>Coating peel strength</b>		$\geq 2.5\text{N}/25\text{mm}$	
<b>Whiteness</b>		$\geq 88$	
<b>Glossiness</b>		$\geq 85$	
<b>Compatible ink</b>		ECO-solvent,Solvent,Latex,UV	
<b>Width</b>	m	0.914m,1.067m,1.27m,1.37m,1.52m	
<b>Temperature Resistance</b>	°C	-20~70	DIN53357 BS3425 Method10
<b>Shelf Time</b>		1 year (Indoor temp.22°C, Relative humidity: 50-55%)	