

#108 Economy Clear Lamination

Dirección: Calle 21 #65 - 47

Teléfono: (4) 235 4433

Celular: 314 700 7638

www.granpapel.com.co

Backing Biaxially Oriented Polypropylene

Adhesive Emulsion Acrylic

| | US Units | Metric Units | | Test Method |
|-----------------------|--|------------------------------|-----------------------|-------------|
| Total Thickness | $0.95 \pm 0.12 \text{ mil}$ | $0.024 \pm 0.003 \text{ mm}$ | | PSTC - 133 |
| Film | 0.75 ± 0.04 mil | 0.019 ± 0.001 mm | | PSTC - 133 |
| Adhesive | 0.20 ± 0.08 mil | 0.005 ± 0.002 mm | | PSTC - 133 |
| 180° Peel Adhesion | ≥ 12 oz/in | ≥ 0.136 kgs/cm | | ASTM D-1000 |
| Tensile Strength | ≥ 12 lbs/in | ≥ 2.16 kg/cm | | PSTC - 131 |
| Elongation | 80 % ~ 180 % | | PSTC - 131 | |
| Temperature Range | Application Temperature | | Operating Temperature | |
| | 32 °F to 150°F | | 0 °F to 175°F | |
| Special Features | Chemical and abrasion resistant | | | |
| Storage Condition: | One year shelf life from date of dispatch if stored at room temperature and humidity levels. | | | |
| Regulation Compliance | Complies with FDA regulations 21CFR 177.1520 & 21CFR 175.105 | | | |

Economy glossy lamination. Great for all purpose label applications.

Important Notice:

The above propertities are approximate and should only provide references and be considered typical only. The accuracy and completeness are not guaranteed. User shall determine suitability of the product for its intended use and user assumes all risk and liability whatsoever in connection therewith. The seller limits its obligation to replacement or at its option, reimbursement of the purchase price of products shown to the seller's satisfaction to have been defective at the time the seller sold it.